

Flowing Consistency:	Syrup
Full KG Consistency:	Typical Paste
EHC KG Consistency:	Thicker Paste
Mix Ratio:	1% – 3% BPO
Gel Time:	4-6 minutes
Cure Time:	15-25 minutes
Shelf Life:	1 year
Location:	Indoor
Use With:	Natural and Engineered Stones
Flowing – Use for:	Laminating, Rodding, Crack/Chip Repair
Full KG – Use for:	Seaming, Laminating, Miterring, Crack/Chip Repair
EHC KG – Use for:	Seaming, Laminating, Miterring, Crack/Chip Repair