

Consistency:	SV-1 Syrup / Pourable
Consistency:	SV-9 Thick Paste
Mix Ratio:	1% – 3% BPO
Gel Time:	3 – 4 minutes
Cure Time:	20 minutes
Shelf Life:	SV-1 / 6 mos. – SV-9 / 6 mos.
Location	Indoor
Use With:	Natural and Engineered Stones
SV-1 Uses:	Laminating, Rodding, Crack Repair, Chip Repair
SV-9 Uses:	Seaming, Laminating, Miter Joints, Crack Repair, Chip Repair