



Category > Strengthen

3D SF

Silicate-Free Densifier



Product Description

Ameripolish® 3D SF Densifier introduces a new non-silicate for superior densification performance. With revolutionary ion-exchange chemistry, Ameripolish® 3D SF offers dramatically improved abrasion resistance, stain resistance, and water repellency over conventional silicate desifiers. This product fully penetrates varying densities of concrete regardless of region or hardness. 3D SF is ideal for use on exposed and polished concrete, as well as cements with integral color.

Features

- Revolutionary Ion-Exchange Chemistry
- Great for grind and seal or traditional polishing jobs
- Hardens deep within the slab to improve durability even after grinding
- Improved abrasion & stain resistance over conventional silicate densifiers
- Enhances polished color, gloss, and clarity
- Contains stain-resistant chemicals to help prevent penetration of stains
- Minimizes dust for healthier indoor air quality
- Provides superior stain resistance especially when combined with SR^{2™} Sealer

Uses

Ameripolish® 3D SF can be used by itself or with Ameripolish® dyes and stain protectors.

- Harden concrete surfaces
- Prepares surface for high gloss diamond polishing
- Locks in dyes for longer lasting color
- Improves resistance to staining
- Improves scratch resistance
- Extends Ameripolish® SR^{2™} coverage rates

Dilution & Coverage

Ameripolish® 3D SF is shipped ready to use (RTU) and should not be mixed with other products. Ameripolish® 3D SF covers 500-700ft² depending on concrete porosity.

Application (Polished Concrete Method)

1. Perform main grind using up to 200-grit resin or equivalent

Product Specification

Application:Spray and Ameripolish® Microfiber PadAppearance:Clear LiquidVOC:Compliant (1g/l)Shelf life:1 yearSolvent:Water-Based

Packaging Specification

Product #	Shipping Wt.	Container
3DSF-5	48 lbs.	5 gallons RTU





Last Updated: 2022.December.06 | Page 2 of 3



Category > Strengthen

3D SF

Silicate-Free Densifier



resin bond diamond.

- 2. Remove all dust and debris using an automatic floor scrubber and fresh water. Allow time to dry.
- 3. Spray 3D SF with overlapping circular motion. Lightly use pad applicator fitted with Ameripolish® Microfiber Pad to spread evenly on surface. Product does not need vigorous scrubbing-in and will not form a gel. As product is absorbed into surface, apply additional product as needed until floor starts to reject the product. Keep floor wet for 15 minutes, spreading with mop to avoid puddles. Allow time to dry.
- 4. Grind up to a 400-resin bond diamond or equivalent.
- 5. Apply additional light application (optional) using Ameripolish® Microfiber Pad.
- Clean tools and equipment with fresh water before product dries. Overspray and unprotected surfaces should be immediately washed off with fresh water. Allow time to dry.
- 7. Polish to the desired grit level.
- 8. Apply Ameripolish® SR^{2™} or 3D SP[™] following manufacturer's instructions to complete protection and enhance appearance.
- Surface should be cleaned regularly using an automatic floor scrubber with Ameripolish® Rejuvenating Cleaner Concentrate, mixed with water according to manufacturer's directions.

Cleanup

Ameripolish® 3D SF washes up quickly with soap and water.

Storage

- Store upright in safe dry place at 40-105F^o (4 -41C^o)
- Keep product from freezing
- Keep out of reach of children
- Seal container after use
- Do not mix with other chemicals

VOC Compliance

In addition, Ameripolish® 3D SF offers VOC compliance with low VOC at 1 g/L and is also compliant with national, state, and district regulations:

- US Environmental Protection Agency
- California Air Resources Board SCM Districts*
- South Coast Air Quality Management District*
- Maricopa County, AZ

Northeast Ozone Transport Commission

*Before application, verify product conformance with local and state codes.

Warning & Safety Information

KEEP OUT OF REACH OF CHILDREN. DO NOT TAKE INTERNALLY. BEFORE USING THIS PRODUCT PLEASE READ THE SAFETY DATA SHEET IN ITS ENTIRETY! Safety Data Sheets (SDS) can be found online at www.ameripolish.com or upon request by contacting Ameripolish at 1-800-592-9320.

SURFACES MUST BE CLEAN AND DRY BEFORE APPLICATION OF THE DYE. NEW SLABS MUST HAVE CURED FOR AT LEAST 28 DAYS BEFORE APPLICATION. For best results perform a moisture content test on both newly-poured and existing slabs. Slabs with a moisture content of 5 lbs per foot or less show best performance (calcium chloride test per ASTM F1869.) High moisture levels may affect performance of color. Do not apply if concrete is frozen, dirty, or has standing water. Test surface absorbency with a light water spray – concrete surface should wet uniformly. If concrete does not wet uniformly, remove any surface contaminants with appropriate cleaning treatment or mechanical process.

Warranty

The information contained herein is believed to be reliable. This information is based on laboratory testing and results. Because of variations in methods, conditions and equipment, each user must test this product to make a judgment of performance. Applicator is responsible for testing material for effectiveness and performance. Manufacturer obligation is limited to the refund of purchase price or replacement of material if proven to be defective. Claims must be made in writing and received within one year from date of product sale to original buyer. Sole remedy shall be replacement of product proven defective.





Category > Strengthen

3D SFSilicate-Free Densifier

