

Category > Protect

## SR<sup>2</sup> WB

### Water Based Fully Penetrating Stain Resistor

#### Product Description

Ameripolish® SR<sup>2</sup> WB is a water-based penetrating stain repellent specifically formulated to protect polished, dyed and non-dyed concrete from oil and water-based stains. The water and oil repelling qualities of SR<sup>2</sup> WB provides superior stain protection on most substrates. SR<sup>2</sup> WB can be used as a standalone product but, to obtain optimum performance, Ameripolish® SR<sup>2</sup> WB is recommended for use with Ameripolish® 3D HS or HSL Densifiers.

#### Features

- Great alternative where solvent-based products are not applicable
- VOC exempt & non-flammable
- Economical penetrating sealer alternative
- Non-topical, penetrating sealer
- Treated surfaces 'breathe' and do not trap moisture
- Excellent stain repellency for residential, commercial, and even industrial applications
- Extreme hydrophobic and oleophobic characteristics for maximum stain resistance
- For pedestrian, vehicular, and high traffic areas
- Durable protection
- High coverage rate
- Typically no impact on substrate color
- Compatible with silicate densifiers, dyes, and integral colorants
- Longer "window of opportunity" for cleaning spills

#### Uses

Ameripolish® SR<sup>2</sup> WB is ideal to be used on:

- New or existing polished concrete
- Exposed concrete flooring

#### Dilution & Coverage

Ameripolish® SR<sup>2</sup> WB is shipped Ready to Use (RTU) and should not be mixed with any other chemical. Approximate coverage rate is 2,000 - 3,000 sqft per gallon.

#### Product Specification

<b>Application:</b>	Spray and Ameripolish® Microfiber Pad
<b>Appearance:</b>	Clear
<b>VOC:</b>	Compliant (3.5g/l)
<b>Shelf life:</b>	1 year
<b>Solvent:</b>	Proprietary (non-hazardous)

#### Packaging Specification

Product #	Shipping Wt.	Container
SR2WB-1	10 lbs.	1 gallon RTU
SR2WB-5	50 lbs.	5 gallons RTU
SR2WB-30	300 lbs.	30 gallons RTU
SR2WB-55	550 lbs.	55 gallons RTU
SR2WB-250	2,500 lbs.	250 gallons RTU



Category > Protect

## SR<sup>2</sup> WB

### Water Based Fully Penetrating Stain Resistor

#### Preparation

Using broom, dust mop or vacuum, remove loose grit and other materials from floor prior to using SR<sup>2</sup> WB.

Use product with air and surface temperatures of 40-90°F (4-32°C); do not apply product outside of these ranges. Avoid application in high winds.

#### Application

Read and fully understand “Preparation” and “Safety Information” prior to application of product. Always test surfaces for desired results prior to commencing work. Recommended method of application is with a low-pressure (40 psi or less) pump sprayer and a conical tip, with a microfiber pad and applicator.

1. Apply in one continuous application. Apply enough product to keep surface wet for approximately 2 to 3 minutes.
2. Spread product with a microfiber pad and applicator and allow drying. Do not allow product to pool or puddle.
3. If needed, burnish surface with a 3000-grit or higher high-speed diamond-impregnated maintenance pad.
4. On extremely porous surfaces, another coat may be required to provide optimum surface protection. Apply after initial coat is dry and burnished.

Drying time: Light foot traffic may be allowed a minimum 1 hour after product has dried. Surfaces should be protected from excessive moisture and vehicular traffic for minimum 8 hours after application. Resistance to oils and acids begin 24 hours after application and full resistance is typically achieved in 7 days.

#### Cleanup

Clean tools and equipment immediately with mineral spirits or equivalent cleaning solvent. Always remove rundown and spills immediately.

#### Maintenance

Remove staining agents from treated areas as soon as possible. Etching may occur from acidic substances, though can typically be repaired with mechanized cleaning equipment. Contact manufacturer for repair recommendations.

Many cleaning agents are destructive to concrete surfaces, even to those treated with SR<sup>2</sup> WB. Ameripolish® recommends Ameripolish® Rejuvenating Cleaner Concentrate as an on-going daily cleaning solution.

#### Storage

- Store upright in safe dry place at 40-110F° (4 -43C°)
- Keep product from freezing
- Keep out of reach of children
- Seal container after use
- Do not mix with other chemicals

#### VOC Compliance

In addition, Ameripolish® SR<sup>2</sup> WB offers VOC compliance with low VOC at 3.5g/L and is also compliant with national, state and district regulations:

- US Environmental Protection Agency
- California Air Resources Board SCM Districts\*
- South Coast Air Quality Management District\*
- Maricopa County, AZ
- Northeast Ozone Transport Commission\*

\*Before application, verify product conformance with local and state codes.

#### Warning & Safety Information

**KEEP OUT OF REACH OF CHILDREN. DO NOT TAKE INTERNALLY. BEFORE USING THIS PRODUCT PLEASE READ THE SAFETY DATA SHEET IN ITS ENTIRETY! Safety Data Sheets (SDS) can be found online at [www.ameripolish.com](http://www.ameripolish.com) or upon request by contacting Ameripolish at 1-800-592-9320.**

Category > Protect

## **SR<sup>2</sup> WB**

**Water Based Fully Penetrating Stain Resistor**

### **Warranty**

The information contained herein is believed to be reliable. This information is based on laboratory testing and results. Because of variations in methods, conditions and equipment, each user must test this product to make a judgment of performance. Applicator is responsible for testing material for effectiveness and performance. Manufacturer obligation is limited to the refund of purchase price or replacement of material if proven to be defective. Claims must be made in writing and received within one year from date of product sale to original buyer. Sole remedy shall be replacement of product proven defective.